



Vero

VeroWhite - FullCure830

Property	ASTM	Metric		Imperial	
Tensile Strength	D-638-03	MPa	49.8	psi	7221
Modulus of Elasticity	D-638-04	MPa	2495	psi	361775
Elongation at Break	D-638-05	%	20	%	20
Flexural Strength	D-790-03	MPa	74.6	psi	10817
Flexural Modulus	D-790-04	MPa	2137	psi	309865
Izod Notched Impact	D-256-06	J/m	24.1	ft lb/in	0.45
Shore Hardness	Scale D	Scale D	83	Scale D	83
Rockwell Hardness	Scale M	Scale M	81	Scale M	81
HDT at 0.45 MPa	D-648-06	C°	43	F°	109
HDT at 1.82 MPa	D-648-07	C°	40	F°	104
Tg	DMA, E"	C°	58	F°	136
Ash Content	NA	%	<0.4	%	<0.4
Water Absorption	D570-98 24 Hr	%	1.15	%	1.15

